

Thang Kiang Nam Quarry Limestone Specification	
CaO	55.0 %
*equivalent to CaCO₃	98.2 %
MgO	0.65%
*equivalent to MgCO₃	1.36%
Acid Insoluble	0.07%
SiO₂	0.01%
Fe₂O₃	0.03%
*Al₂O₃	0.04%
*LOI	42.5%

Thang Kiang Nam Quarry Limestone Analyze

<u>% Brightness</u> <u>(BISO 2470)</u>	<u>% Whiteness Index</u> <u>(ASTM E 313)</u>	<u>% Yellow Index</u> <u>(ASTM E 313)</u>
92.5	86.8	2.02